

Argile naturelle extraite de notre carrière, préparée à l'ancienne.
Adaptée à toutes les techniques.

 Natural clay extracted from our quarry, prepared the old-fashioned way. Suitable for all techniques.	 Arcilla natural extraída de nuestra cantera, preparada a la antigua usanza. Apta para todas las técnicas.	 Argilla naturale estratta dalla nostra cava, preparata alla vecchia maniera. Adatta a tutte le tecniche.	 Natürliche Ton, die in unserer Grube abgebaut und auf althergebrachte Weise zubereitet wird. Für alle Techniken geeignet.
--	---	--	---

Données

Techniques

T °C Dégourdi :	1 000 °C
T °C Cuisson :	1 290 - 1 300 °C
Retrait séchage :	5,00 %
Retrait cuisson	6,00 %
Absorption d'eau :	2,00 %
Coefficient de dilation :	52 x 10 ⁻⁷ entre 0-500 °C
Indice de plasticité	21,32 %

Chimiques

SiO₂	71,01
Al₂O₃	23,31
Fe₂O₃	2,19
TiO₂	1,11
CaO	0,32
MgO	0,49
Na₂O	0,12
K₂O	1,45

Pain de 10 kg | 100 unités par palette | poids total 1000 kg